FINIXA®
paint processing products

Stone chip repair UV

SCU 20

Fast UV curing clear coat for stone chip and scratch repair

Fast, simple and cost effective repair of stone chips and scratches
1-component, fast curing
No shrinkage after curing
High level of finish
Same strength, durability and chemical resistance as a 2K clear coat
Can be sanded and polished after 45 seconds
Curing with stone chip curing lamp SCL 00

The perfect stone chip repair in 10 easy steps :

1. Clean/degrease the surface with TSP 600 Foam-it!
2. Sand around the stone chip with SPDM P1500-2000
3. Clean with TSP 600 Foam-it!
4. Apply the base coat
5. Dry the base coat
6. Apply stone chip repair UV with PMP touch-up tips
7. Dry for 45 seconds at 20mm. distance with stone chip curing lamp
8. Remove excess clear coat with DRF 10 dust removal file
9. Sand with SPDR P1500-2000
10. Polish with Finixa polishing system



Code	Description	Box	Pal
SCU 20	Stone chip repair UV	12	X

Chemicar Europe
Baarbeek 2
2070 Zwijndrecht
Belgium

T.: +32 32 34 87 80
F.: +32 32 34 87 89
www.finixa.com
info@finixa.com